

| Names of indicators, units                                                                                         | Test method           | CASTROL | CASTROL + 0,6 % NeoProtec | LIQUI MOLY | LIQUI MOLY + 0,6 % NeoProtec | ARAL | ARAL + 0,6 % NeoProtec |
|--------------------------------------------------------------------------------------------------------------------|-----------------------|---------|---------------------------|------------|------------------------------|------|------------------------|
|                                                                                                                    |                       | C3      |                           |            |                              |      |                        |
| Tribological Testing by 4 Ball Methods at a temperature of (20 ± 5) ° C: - wear indicator (Dz) (196 N, 1 hour), mm | GOST 9490 (DIN 51350) | 0,32    | 0,19                      | 0,28       | 0,17                         | 0,3  | 0,18                   |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - critical load (Pk), N                                |                       | 921     | 1059                      | 1097       | 1184                         | 975  | 1101                   |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - index badass, N                                      |                       | 412     | 472                       | 501        | 556                          | 503  | 558                    |

| Names of indicators, units                                                                                         | Test method           | ZIC  | ZIC + 0,6 % NeoProtec | XADO  | XADO + 0,6 % NeoProtec | ELF  | ELF + 0,6 % NeoProtec |
|--------------------------------------------------------------------------------------------------------------------|-----------------------|------|-----------------------|-------|------------------------|------|-----------------------|
|                                                                                                                    |                       | C3   |                       | A3/B4 |                        |      |                       |
| Tribological Testing by 4 Ball Methods at a temperature of (20 ± 5) ° C: - wear indicator (Dz) (196 N, 1 hour), mm | GOST 9490 (DIN 51350) | 0,54 | 0,26                  | 0,3   | 0,17                   | 0,3  | 0,17                  |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - critical load (Pk), N                                |                       | 921  | 1004                  | 784   | 956                    | 1164 | 1245                  |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - index badass, N                                      |                       | 409  | 466                   | 440   | 501                    | 486  | 549                   |

| Names of indicators, units                                                                                         | Test method           | MOBIL | MOBIL + 0,6 % NeoProtec | SHELL | SHELL + 0,6 % NeoProtec | ADDINOL | ADDINOL + 0,6 % NeoProtec |
|--------------------------------------------------------------------------------------------------------------------|-----------------------|-------|-------------------------|-------|-------------------------|---------|---------------------------|
|                                                                                                                    |                       | A3/B4 |                         |       |                         |         |                           |
| Tribological Testing by 4 Ball Methods at a temperature of (20 ± 5) ° C: - wear indicator (Dz) (196 N, 1 hour), mm | GOST 9490 (DIN 51350) | 0,38  | 0,22                    | 0,27  | 0,16                    | 0,3     | 0,18                      |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - critical load (Pk), N                                |                       | 1038  | 1121                    | 1097  | 1185                    | 1098    | 1196                      |
| Lubricating properties by at a temperature of (20 ± 5) ° C: - index badass, N                                      |                       | 490   | 553                     | 501   | 556                     | 498     | 554                       |